

# Synolite™ 1967-G-9

## Low shrinkage DCPD resin, yielding great surface quality in Vacuum infusion

Synolite™ 1967-G-9 is a low viscous unsaturated DCPD based polyester resin ideally suited for Vacuum infusion. The low resin shrinkage results in components with great surface quality.

The resins allows for making components with high fiber loading and hence great strength and stiffness.

### Benefits

- Great surface quality
- Easy injection because of low viscosity
- DNV approved
- Long gel time for making large components
- Track record of performance

## Major Applications

Synolite™ 1967-G-9 is recommended for injection applications with foil as top-mold to produce high performance constructional laminates. Synolite™ 1967-G-9 can be used with all commonly used types of glass reinforcement to produce boats, bridges, tanks, vehicles, constructions in sea water etc.

Synolite™ 1967-G-9 is a medium reactive resin with a low peak exotherm and relatively low shrinkage. Due to a good through-cure it can be used for thick and thin laminates. Synolite™ 1967-G-9 has very good fiber wetting and impregnation properties.

## Certifications and Approvals

This resin has a Det Norske Veritas approval, grade 2 for boat building.

### Product Specifications

Property	Value	Unit	TM
Gel time	43 - 48	min	TM 2625
Peak temperature	115 - 145	°C	TM 2625
Peak time	54 - 68	min	TM 2625
Viscosity	135 - 165	mPa.s	TM 2013, 23 °C, 100 s <sup>-1</sup>
Appearance	Clear		TM 2265
Solids content	60 - 63	%	TM 2033

Viscosity measurement TM 2013 at 23°C: Physica, spindle Z2, shear rate 100 s<sup>-1</sup>, 23°C.

Curing conditions TM 2625, 25°C: 3.0 g Medium reactive Methyl Ethyl Ketone Peroxide (MEKP) in 100 g resin.

### Liquid resin typical properties

Property	Value	Unit	TM
Density	1080	kg/m <sup>3</sup>	TM 2160, 20 °C
Flash point	33	°C	TM 2800
Stability	6	Month	TM 2303, 25 °C, dark

### Unfilled castings typical properties

Property	Value	Unit	TM
Tensile elongation	2.3	%	ISO 527-2
Flexural modulus	3.8	GPa	ISO 178
HDT	85	°C	ASTM D648 264 psi
Tensile strength	70	MPa	ISO 527-2
Tensile modulus	3.8	GPa	ISO 527-2
Flexural strength	130	MPa	ISO 178
Impact strength	15	kJ/m <sup>2</sup>	ISO 179

Cured with 1% Medium reactive Methyl Ethyl Ketone Peroxide (MEKP). Post cured 24 h at RT followed by 24 h at 70°C.

### Storage Guidelines

The resin should be stored indoors in a dry place at temperatures between 5°C and 30°C, in the original, unopened, 100% light-tight and undamaged packaging.

The properties of the resin may change slightly during storage. Shelf life is shorter at higher temperatures.

### Material Safety

A Material Safety Data Sheet of this product is available on request.

## Test Methods

Test methods (TM) referred to in the table(s) are available on request.

## ISO 9001:2015 Certified

The Quality Management Systems at every AOC manufacturing facility have been certified as meeting ISO 9001:2015 standards. This certification recognizes that each AOC facility has an internationally accepted model in place for managing and assuring quality. We follow the practices set forth in this model to add value to the resins we make for our customers.

## AOC. Trusted Solutions

AOC is the leading global supplier of specialty formulations and solutions which enable customers to create robust, durable, and versatile products and components for applications in Coatings and Protective Barriers, Colorants and Visual Effects, Adhesives and Specialties, and conventional Composites. With strong capabilities worldwide in manufacturing and science, the company works closely with customers to deliver unrivaled quality, service, and reliability for today and create innovative solutions for tomorrow.

### Contact us for more information

We will help you choose the right resin solution.

Tel.: + 45 4485 0500  
[web@monofiber.dk](mailto:web@monofiber.dk)

**Monofiber**  
KOMPOSIT INDUSTRIENS BEDSTE BRANDS

**AOC**  
Trusted Solutions

AOC is a registered trademark of the AOC group of companies.

The user is held responsible for checking the quality, safety and all other properties of our products prior to use. The information and recommendations contained herein are to the best of our knowledge accurate and reliable, but no rights whatsoever may be derived by any party other than those expressly agreed to with a selling entity of the AOC group of companies in a legally binding agreement. AOC hereby makes no warranty of any kind, express or implied, including those of merchantability and fitness for purpose. Unless explicitly agreed to in writing by AOC otherwise, all offers, quotations, sales and deliveries of AOC products are subject to the general conditions of sale of AOC. Atlac®, Beyone®, Daron®, NeoMould®, Neoxil®, Palatal®, Palapreg®, Synolite™, the AOC™ name, the AOC™ logo, the NEXT™ logo and the Trusted Solutions™ logo are the registered trademarks of the AOC group of companies

For more information: [aocformulations.com](http://aocformulations.com)