

Synolite™ 1967-G-2

DCPD resin for Vacuum Infusion

Synolite™ 1967-G-2 is a medium viscous unsaturated DCPD based polyester resin.

The resin is particularly suited for use in Vacuum infusion processes. Components made with Synolite™ 1967-G-2 resin can have great surface quality.

Benefits

- Great surface quality associated with low inherent shrinkage
- High process output through short cycle times
- Easy processing
- Performance track record

Certifications and Approvals

This resin can meet Det Norske Veritas, grade 2 for boat building.

Product Specification

Property	Value	Unit	TM
Appearance	Clear		TM 2265
Solids content	62.5 - 65.5	%	TM 2033
Viscosity 23 °C, 100 s ⁻¹	200 - 220	mPa.s	TM 2013
Gel time 25 until 35 °C	42 - 47	min	TM 2625
Peak time	52 - 66	min	TM 2625
Peak temperature	120 - 150	°C	TM 2625

Viscosity measurement TM 2013 at 23°C: Physica, spindle Z2, shear rate 100 s⁻¹, 23°C. Curing conditions TM 2625, 25°C: 3.0 g Medium reactive Methyl Ethyl Ketone Peroxide (MEKP) in 100 g resin.

Major Applications

Synolite™ 1967-G-2 is a medium reactive resin that gives a relatively low peak exotherm. This resin can be used for thick and thin laminates and shows a good through cure and relatively low shrinkage. Synolite™ 1967-G-2 has very good fiber wetting and impregnation properties.

Synolite™ 1967-G-2 resin is recommended for injection applications with foil as top-mold to produce high performance constructional laminates. Synolite™ 1967-G-2 can be used with all commonly used types of glass reinforcement.

Liquid resin typical properties

Property	Value	Unit	TM
Density 23 °C	1120	kg/m ³	TM 2160
Flash point	33	°C	TM 2800
Stability Solid dark 25 °C	6	month	
Color	Brown	-	

Unfilled castings typical properties

Property	Value	Unit	TM
Density 23 °C	1155	kg/m ³	DIN 53479
Tensile strength	70	MPa	ISO 527-2
Tensile modulus	3.8	GPa	ISO 527-2
Elongation at break	2.3	%	ISO 527-2
Flexural strength	130	MPa	ISO 178
Flexural E-Modulus	3.8	GPa	ISO 178
HDT ISO 75 Ae	85	°C	ISO 75 Ae
Impact strength	15	kJ/m ²	ISO 179

Cured with 1% Medium reactive Methyl Ethyl Ketone Peroxide (MEKP). Post cured 24 h at RT followed by 24 h at 70°C.

Application Guidelines

Before use, the resin should be conditioned at a well-defined, application dependent temperature (usually 15°C minimum for a MEKP / Cobalt cure).

Storage Guidelines

The resin should be stored indoors in the original, unopened and undamaged packaging, in a dry place at temperatures between 5°C and 25°C and the properties might change during storage. Shelf life is reduced at higher temperatures and the properties of the resin might change during storage.

The shelf life of monomer containing unsaturated polyesters will be significantly reduced when exposed to light. Store in dark and in 100% light tight containers only.

For DCPD resins it is known that skin formation occurs when exposed to air ventilation or replacement from the original packaging.

Material Safety

A Safety Data Sheet (SDS) of this product is available on request.

Test Methods

Test methods (TM) referred to in the table(s) are available on request.

ISO 9001:2015 Certified

The Quality Management Systems at every AOC manufacturing facility have been certified as meeting ISO 9001:2015 standards. This certification recognizes that each AOC facility has an internationally accepted model in place for managing and assuring quality. We follow the practices set forth in this model to add value to the resins we make for our customers.

AOC. Trusted Solutions

AOC is the leading global supplier of resins and specialty materials which enable customers to create robust, durable and versatile products and components. With strong capabilities around the world in manufacturing and science, the company works closely with customers to deliver unrivaled quality, service, and reliability for today, and create innovative solutions for tomorrow. Partner with AOC and we will work together to find the right solutions for your business.

Contact us for more information

We will help you choose the right resin solution.

Tel.: + 45 4485 0500
web@monofiber.dk

Monofiber
KOMPOSIT INDUSTRIENS BEDSTE BRANDS

AOC
Trusted Solutions

AOC is a registered trademark of the AOC group of companies.

The user is held responsible for checking the quality, safety and all other properties of our products prior to use. The information and recommendations contained herein are to the best of our knowledge accurate and reliable, but no rights whatsoever may be derived by any party other than those expressly agreed to with a selling entity of the AOC group of companies in a legally binding agreement. AOC hereby makes no warranty of any kind, express or implied, including those of merchantability and fitness for purpose. Unless explicitly agreed to in writing by AOC otherwise, all offers, quotations, sales and deliveries of AOC products are subject to the general conditions of sale of AOC. Altek®, Atlac®, Beyone®, Daron®, FirePel®, NeoMould®, Neoxil®, Palatal®, Palapreg®, Pultru®, Synolite™, Vipel®, the AOC™ name, the AOC™ logo and the Trusted Solutions™ logo are the registered trademarks of the AOC group of companies

For more information: aocresins.com