

## TECHNICAL DATASHEET

**SAP No.** 30005256 **Article Description** Y-E-837g/m<sup>2</sup>-1270mm

**Textile Structure** 7000133 **SAERTEX®**

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	0 °	425 g/m <sup>2</sup>	+/- 5,0 %	E-glass 1.200 TEX
2	45 °	200 g/m <sup>2</sup>	+/- 5,0 %	E-glass 300 TEX
1	-45 °	200 g/m <sup>2</sup>	+/- 5,0 %	E-glass 300 TEX
<b>Stitching</b>		12 g/m <sup>2</sup>	+/- 3 g/m <sup>2</sup>	PES [Polyester] 76 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

<b>Gauge</b>	10,0	<b>Stitching pattern</b>	tricot-warp	<b>Width (nominal)</b>	1270 mm
<b>Stitch length</b>	2,60 mm	<b>Total tolerance</b>	+/- 5,3 %	<b>Total areal weight</b>	837 g/m <sup>2</sup>

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage** With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.