



TECHNICAL DATASHEET

SAP No. 30007516 Article Description Y-E-933g/m²-1270mm

Textile Structure 7005393 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)									
Layer	Construction	Areal weight	Tolerance	Material					
3	0	425 g/m²	+/- 3,0 %	E-glass 1.200 TEX					
2	45	251 g/m²	+/- 3,0 %	E-glass 300 TEX					
1	-45	251 g/m²	+/- 3,0 %	E-glass 300 TEX					
Stitching		6 g/m²	+/- 1 g/m²	PES [Polyester] 76 dtex					

Fiber input can be determined individually

FURTHER CHARACTERISTICS									
Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1270 mm				
Stitch length	2,60 mm	Total tolerance	+/- 3,1 %	Total areal weight	933 g/m²				
	,		,	J					

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on

the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging

options can be determined individually.

Storage Keep in original packaging. Store in a dry environment. Avoid direct sunlight.

(recommendation) Fabrics to be kept under processing conditions at least 24 hours

prior to use to avoid problems with humidity and electrostatic charge.

-