

TECHNICAL DATASHEET

SAP No. 30007622 Article Description B-E-625g/m²-1270mm

Textile Structure 7007696 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

| Layer | Construction | Areal weight | Tolerance | Material |
|-----------|--------------|----------------------|------------------------|-------------------------|
| 2 | 0 | 331 g/m ² | +/- 5,0 % | E-glass 1.200 TEX |
| 1 | 90 | 288 g/m ² | +/- 5,0 % | E-glass 600 TEX |
| Stitching | | 6 g/m ² | +/- 1 g/m ² | PES [Polyester] 76 dtex |

Fiber input can be determined individually

FURTHER CHARACTERISTICS

| | | | | | |
|---------------|---------|-------------------|-------------|--------------------|----------------------|
| Gauge | 5,0 | Stitching pattern | tricot-warp | Width (nominal) | 1270 mm |
| Stitch length | 3,50 mm | Total tolerance | +/- 5,1 % | Total areal weight | 625 g/m ² |

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage (recommendation) Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.