



## TECHNICAL DATASHEET

SAP No. 30007628 Article Description Q-E-1184g/m<sup>2</sup>-1270mm

Textile Structure 7007700 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)								
Layer	Construction	Areal weight	Tolerance	Material				
4	0 。	295 g/m²	+/- 5,0 %	E-glass 600 TEX				
3	45	300 g/m²	+/- 5,0 %	E-glass 300 TEX				
2	90	283 g/m²	+/- 5,0 %	E-glass 600 TEX				
1	-45	300 g/m²	+/- 5,0 %	E-glass 300 TEX				
Stitching		6 g/m²	+/- 1 g/m²	PES [Polyester] 76 dtex				

Fiber input can be determined individually

(recommendation)

FURTHER CHARACTERISTICS								
Gauge	5,0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm			
Stitch length	2,60 mm	Total tolerance	+/- 5,1 %	Total areal weight	1184 g/m²			

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on

the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging

options can be determined individually.

Storage Keep in original packaging. Store in a dry environment. Avoid direct sunlight.

Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.

-