

TECHNICAL DATASHEET

SAP No. 30007904 Article Description B-C-306g/m²-1270mm

Textile Structure 7007924

SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
2	0	150 g/m ²	+/- 5,0 %	ZOLTEK PANEX 35-13 50K
1	90	150 g/m ²	+/- 5,0 %	ZOLTEK PANEX 35-13 50K
Stitching		6 g/m ²	+/- 1 g/m ²	PES [Polyester] 76 dtex

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,2 %	Total areal weight	306 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.