

## TECHNICAL DATASHEET

SAP No. 30013730 Article Description Q-C-806g/m<sup>2</sup>-1270mm

Textile Structure 7010179 SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	200 g/m <sup>2</sup>	+/- 5,0 %	ZOLTEK PANEX 35-13 50K
3	-45°	200 g/m <sup>2</sup>	+/- 5,0 %	ZOLTEK PANEX 35-13 50K
2	90	200 g/m <sup>2</sup>	+/- 5,0 %	ZOLTEK PANEX 35-13 50K
1	45	200 g/m <sup>2</sup>	+/- 5,0 %	ZOLTEK PANEX 35-13 50K
Stitching		6 g/m <sup>2</sup>	+/- 1 g/m <sup>2</sup>	PES [Polyester] 76 dtex

### FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,1 %	Total areal weight	806 g/m <sup>2</sup>

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage (recommendation) Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.