

TECHNICAL DATASHEET

SAP No. 30000341 Article Description Q-E-986g/m²-1270mm

Textile Structure 7000171 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	236 g/m ²	+/- 5,0 %	E-glass 600 TEX
3	45 °	251 g/m ²	+/- 5,0 %	E-glass 300 TEX
2	90 °	236 g/m ²	+/- 5,0 %	E-glass 600 TEX
1	-45 °	251 g/m ²	+/- 5,0 %	E-glass 300 TEX
Stitching		12 g/m ²	+/- 3 g/m ²	PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	10,0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,2 %	Total areal weight	986 g/m ²

- Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.
- Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.
- Storage** With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.