

## TECHNICAL DATASHEET

SAP No. 30000944 Article Description Q-E-820g/m<sup>2</sup>-1270mm

Textile Structure 7001689 SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	213 g/m <sup>2</sup>	+/- 5,0 %	E-glass
3	45 °	200 g/m <sup>2</sup>	+/- 5,0 %	E-glass
2	90 °	201 g/m <sup>2</sup>	+/- 5,0 %	E-glass
1	-45 °	200 g/m <sup>2</sup>	+/- 5,0 %	E-glass
Stitching		6 g/m <sup>2</sup>	+/- 1 g/m <sup>2</sup>	synthetic

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	2,02 mm	Total tolerance	+/- 5,1 %	Total areal weight	820 g/m <sup>2</sup>

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage** With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.