

TECHNICAL DATASHEET

SAP No. 30003551 Article Description X-E-298g/m²-1270mm

Textile Structure 7004168 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	45 °	145 g/m ²	+/- 3,0 %	E-glass 200 TEX
2	0 °	2 g/m ²	+/- 3,0 %	E-glass 68 TEX
1	-45 °	145 g/m ²	+/- 3,0 %	E-glass 200 TEX
Stitching		6 g/m ²	+/- 1 g/m ²	PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	warp	Width (nominal)	1270 mm
Stitch length	3,00 mm	Total tolerance	+/- 3,3 %	Total areal weight	298 g/m ²

Tracer yarn¹ 2 PC blue & tracer yarn 2 PC yellow

¹Position can be determined individually

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.