

TECHNICAL DATASHEET

SAP No. 30007516 **Article Description** Y-E-933g/m²-1270mm

Textile Structure 7005393 **SAERTEX®**

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	0 °	425 g/m ²	+/- 3,0 %	E-glass
2	45 °	251 g/m ²	+/- 3,0 %	E-glass
1	-45 °	251 g/m ²	+/- 3,0 %	E-glass
Stitching		6 g/m ²	+/- 1 g/m ²	synthetic

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1270 mm
Stitch length	2,60 mm	Total tolerance	+/- 3,1 %	Total areal weight	933 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.