



TECHNICAL DATASHEET

SAP No. 30007629 Article Description X-E-996g/m²-1270mm

Textile Structure 7005052 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)								
Layer	Construction	Areal weight	Tolerance	Material				
3	45 °	494 g/m²	+/- 5,0 %	E-glass				
2	0°	2 g/m²	+/- 5,0 %	E-glass				
1	-45 °	494 g/m²	+/- 5,0 %	E-glass				
Stitching		6 g/m²	+/- 1 g/m²	synthetic				

Fiber input can be determined individually

FURTHER CHARACTERISTICS								
Gauge	5,0	Stitching pattern	warp	Width (nominal)	1270 mm			
Stitch length	2,60 mm	Total tolerance	+/- 5,1 %	Total areal weight	996 g/m²			

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on

the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging

options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight.

To avoid problems with humidity and electrostatic charge, fabrics to be

conditioned 24 hours prior to processing, independent of storage conditions.