

## TECHNICAL DATASHEET

SAP No. 30008091 Article Description SAERflow BE600/BX304/150 - 1270mm

Textile Structure 7008069 SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
7	0 °	283 g/m <sup>2</sup>	+/- 5,0 %	E-glass
6	90 °	283 g/m <sup>2</sup>	+/- 5,0 %	E-glass
5	0 °	10 g/m <sup>2</sup>	+/- 5,0 %	E-glass
4	45 °	134 g/m <sup>2</sup>	+/- 5,0 %	- Hybrid Glass
3	0 °	10 g/m <sup>2</sup>	+/- 5,0 %	E-glass
2	45 °	134 g/m <sup>2</sup>	+/- 5,0 %	- Hybrid Glass
1	CSM	150 g/m <sup>2</sup>	+/- 10,0 %	E-glass
Stitching		6 g/m <sup>2</sup>	+/- 1 g/m <sup>2</sup>	synthetic

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,8 %	Total areal weight	1010 g/m <sup>2</sup>

Tracer yarn<sup>1</sup> 3 PC light brown

<sup>1</sup>Position can be determined individually

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage** With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.