

TECHNICAL DATASHEET

SAP No. 30000122 Article Description B-S-E-931g/m²-1300mm

Textile Structure 7000077 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	0 °	331 g/m ²	+/- 5 %	E-glass 1.200 TEX
2	90 °	288 g/m ²	+/- 5 %	E-glass 600 TEX
1	CSM	300 g/m ²	+/- 10 %	E-glass
Stitching		12 g/m ²	+/- 3 g/m ²	PES [Polyester] 110 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	7,0	Stitching pattern	tricot-warp	Width (nominal)	1.300 mm
Stitch length	3,50 mm	Total tolerance	6,9 %	Total areal weight	931 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage recommendation With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.