

## TECHNICAL DATASHEET

**SAP No.** 30000383 **Article Description** Q-E-1232g/m<sup>2</sup>-1270mm

**Textile Structure** 7000200 **SAERTEX®**

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	319 g/m <sup>2</sup>	+/- 5 %	E-glass 900 TEX
3	45 °	300 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
2	90 °	307 g/m <sup>2</sup>	+/- 5 %	E-glass 600 TEX
1	-45 °	300 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX

**Stitching** 6 g/m<sup>2</sup> +/- 1 g/m<sup>2</sup> PES [Polyester] 76 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1.270 mm
Stitch length	2,60 mm	Total tolerance	5,1 %	Total areal weight	1232 g/m <sup>2</sup>

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage recommendation** With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.