

TECHNICAL DATASHEET

SAP No. 30000408 Article Description X-E-444g/m²-1270mm

Textile Structure 7000204 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	45 °	217 g/m ²	+/- 5 %	E-glass 300 TEX
3	90 °	3 g/m ²	+/- 5 %	E-glass 68 TEX
2	0 °	1 g/m ²	+/- 5 %	E-glass 68 TEX
1	-45 °	217 g/m ²	+/- 5 %	E-glass 300 TEX
Stitching		6 g/m ²	+/- 1 g/m ²	PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	warp	Width (nominal)	1.270 mm
Stitch length	2,60 mm	Total tolerance	5,2 %	Total areal weight	444 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage recommendation With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.