

TECHNICAL DATASHEET

SAP No. 30001209 **Article Description** U-E-591g/m²-1200mm

Textile Structure 7000039 **SAERTEX®**

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

| Layer | Construction | Areal weight | Tolerance | Material |
|-----------|--------------|----------------------|------------------------|--------------------------|
| 2 | 0 ° | 520 g/m ² | +/- 5 % | E-glass 1.200 TEX |
| 1 | 90 ° | 54 g/m ² | +/- 5 % | E-glass 68 TEX |
| Stitching | | 17 g/m ² | +/- 3 g/m ² | PES [Polyester] 110 dtex |

Fiber input can be determined individually

FURTHER CHARACTERISTICS

| | | | | | |
|---------------|---------|-------------------|--------|--------------------|----------------------|
| Gauge | 10,0 | Stitching pattern | tricot | Width (nominal) | 1.200 mm |
| Stitch length | 4,00 mm | Total tolerance | 5,4 % | Total areal weight | 591 g/m ² |

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage recommendation With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.