

TECHNICAL DATASHEET

SAP No. 30003201 Article Description U-C-882g/m²-500mm

Textile Structure 7003573 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	85 °	12 g/m ²	+/- 5 %	E-glass 68 TEX
2	0 °	852 g/m ²	+/- 5 %	ZOLTEK PANEX35 50K
1	85 °	12 g/m ²	+/- 5 %	E-glass 68 TEX
Stitching		6 g/m ²	+/- 1 g/m ²	PES [Polyester] 80 dtex

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	warp	Width (nominal)	500 mm
Stitch length	3,55 mm	Total tolerance	5,1 %	Total areal weight	882 g/m ²

Tracer yarn¹ 2 PC red

¹Position can be determined individually

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage recommendation With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.