

TECHNICAL DATASHEET

SAP No. 30003791 Article Description U-C-314g/m²-1230mm

Textile Structure 7003892 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
2	0 °	300 g/m ²	+/- 5,0 %	ZOLTEK PANEX 35-13 50K
1	85 °	11 g/m ²	+/- 5,0 %	E-glass 68 TEX
Stitching		3 g/m ²	+/- 1 g/m ²	PES [Polyester] 33 dtex SC

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	tricot	Width (nominal)	1.230 mm
Stitch length	5,00 mm	Total tolerance	+/- 5,3 %	Total areal weight	314 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendationn and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.